


STEEL FOR TRACK PUNCH
TO CONFORM TO THE FOLLOWING.
CRUCIBLE STEEL
CARBON .70 TO .85
PHOSPHORUS .04 OR UNDER
SULPHUR .04 OR UNDER
MANGANESE .30 TO .35

FRONT VIEW . SIDE VIEW .

TRACK PUNCH .




STEEL FOR RAIL CUTTER
TO CONFORM TO THE FOLLOWING:
CRUCIBLE STEEL
CARBON .70 TO .85
PHOSPHORUS .04 OR UNDER
SULPHUR .04 OR UNDER
MANGANESE .30 TO .35

FRONT VIEW . SIDE VIEW .

RAIL CUTTER .

55614
P. R. R.
STANDARD
TRACK TOOLS .



CORRECT,
Joseph D. Richards
ENGR. M. W.

APPROVED
[Signature]

REVISED DEC. 24, 1903.
PUNCHING EDGE OF TRACK PUNCH.

MARCH 1ST 1894 GENERAL MANAGER .
REVISED FEB. 1906.