





Section at A-B



Section at B-C



STEEL FOR CLAW BARS
to conform to the following:-
OPEN HEARTH STEEL

Carbon	.50 to .60
Phosphorus	.04 or under.
Sulphur	.04 or under.
Manganese	.35 to .50



Section at E-F



Section at C-D



Section at D-E

ORIGINAL ON FILE M.W.

58758
P. R. R. STANDARD
CLAW BAR
FEBRUARY, 1906

0" 1" 2" 3"

DRAWN BY A.E.C.
CHECKED BY G.W.

Correct L. Greiner
ENGINEER M. W.

Approved Joseph J. Richards
CHIEF ENGINEER M. W.

Approved W. W. Atterbury
GENERAL MANAGER

http://PRR.Railfan.net collection of Rob Schoenberg Commercial reproduction prohibited